



Technical Data Sheet

Q 20-017 Uni-Soft Putty

Charakteristics:

20-017 is a universal fill- and fine putty of particularly creamy consistency.

The use of synthetic micro fill ingredients provides this putty its unique processing, combined with a super easy sandability. 20-017 adheres to sheet metal, as well as galvanized zinc.

Application:

The surface must be sanded, clean, dry and free of grease. Mix the putty properly by adding 2-3% BPO Hardener. Process at 20 °C within 4-5 minutes. Higher temperatures shorten the processing time.

Caution:

Hardener under- or overdosing can lead to discoloration in the topcoat.

Technical Data:

Density: 1.76 g / cm³


Color: beige



2004/42/II(b)(250)<250




Clean
60-010



BPO- 2-3%



Pot life
4-5 min 20°C




20 - 30 min 20°C




Hand sanding / dry:
P150 - P320



Excenter / dry:
P150 - P320



Shelf life:
12 Monate



Store at cool
and dry place

Dieses Datenblatt dient nur zu Informationszwecken. Nach unserem Kenntnisstand entsprechen die angegebenen Daten dem neuesten Standard und beruhen auf jahrelanger Erfahrung in der Herstellung unserer Produkte.

Copyright: Q-Company 2019, alle Rechte vorbehalten

Q-Company Int. GmbH / Beckershof 3 / D-24558 Henstedt-Ulzburg / Germany

Version: 02.01.2017