



# Technical Datasheet

## Q 20-100 2K Fibreglass Putty

### Characteristics:

Putty with glass fibres. Easy to work and sand even with a coarse sanding paper (P120 - P150). 2K Fibreglass Putty can be used under filler directly. 2K Fibreglass Putty has been designed for use on steel, aluminium and glass-fibre reinforced plastic. Manual / machine dry sanding. Easy to work also with homogenous surfaces even by applying thick coats. 2K Fibreglass Putty doesn't fill the sanding paper and has very good adhesion. It can be used to reinforce damaged surfaces.

### Application:

The surface must be clean, dry, degreased and matted. Thoroughly mix putty and 2-3% of hardener BPO by weight. Apply within 5 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

### Note:

Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C.

### Technical data:

Density: 1,75 g/cm<sup>3</sup>


Colour: green



2004/42/IIIB(b)(250)<250




Cleaning  
60-010



BPO- 2-3%



Pot life  
3 -5 min 20°C




16 - 30 min 20°C




Hand sanding / dry:  
P120 - P320



Machine sanding / dry:  
P120 - P320



Shelf life:  
12 Month



Store in cool place



Latex / Nitril

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.

Copyright: Q-Company 2017, all rights reserved.

Q-Company Int. GmbH / Beckershof 3 / D-24558 Henstedt-Ulzburg / Germany

Version: 02.01.2017