



Technical Datasheet

Q 20-320 Universal Putty

Characteristics:

Universal putty is designed to adhere on steel, aluminium, zinc coated surfaces and polyester laminates. Due to its excellent thixotropy it has very good shaping properties in any required thickness.

It can also be used as a finishing putty, leaving a smooth surface without pinholes.

For very large unevennesses putty should be applied in several layers. Machine/manual dry sanding.

Application:

The surface must be cleaned, dry, degreased and matted. Thoroughly mix putty with 2-3% of BPO hardener by weight. Apply within 5 minutes at 20°C. Higher temperature can reduce the pot life and accelerate the drying time.

Note:

Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 18°C.

Technical data:

Density: 1,82 g/cm³


Colour: beige



2004/42/II(b)(250)<250




Cleaning
60-010



BPO 2-3%



Pot life
5 min 20°C



20 min. at 20°C




Hand sanding / dry:
P120 - P320



Machine sanding / dry:
P120 - P320



Shelf life:
12 Month



Store in cool place



Latex / Nitril

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.

Copyright: Q-Company 2017, all rights reserved.

Q-Company Int. GmbH / Beckershof 3 / D-24558 Henstedt-Ulzburg / Germany

Version: 02.01.2017