



Technical Datasheet

Q 20-360 G-Multi Polyester Putty -green-

Characteristics:

Multifunctional 2K polyester putty combining creamy textures, high hardness with good elasticity and very soft sanding. Very good adhesion on bare steel, zinc coated and aluminium surfaces as well as polyester laminates. It may be applied in both thin and thick layers.

Application:

The surface must be clean, dry, degreased and matted with abrasives. Thoroughly mix putty by weight with 2% of BPO hardener. Apply within 5 - 6 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note:

Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C. Do not apply the putty directly on the reactive primers, 1K acrylic and nitrocellulose products.

Technical data:

Density: 1,56 - 1,58 g/cm³


Colour: green



2004/42/IIIB(b)(250) <250 g/l




Cleaning
60-010



BPO- 2%



Pot life
5 - 6 min 20°C



Thickness
max. 5 mm




20 - 30 min 20°C




Hand sanding / dry:
P80 - P240



Machine sanding / dry:
P80 - P240



Shelf life:
12 Month



Store in cool place



Latex / Nitril

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.

Copyright: Q-Company 2017, all rights reserved.

Q-Company Int. GmbH / Beckershof 3 / D-24558 Henstedt-Ulzburg / Germany

Version: 02.01.2017