



# Technical Datasheet

## Q 20-800 2K Polyester Multicreme Putty

### Characteristics:

Ultra lightweight polyester putty, characterized by good adhesion to different surfaces; metal, aluminium, galvanized, wood and polyester laminates. Very soft and easy to sand, the density is 45 % lower than traditional putty. For filling in deep uneven areas and dents on motor vehicle bodywork in the area of cars, lorries, buses and railway vehicles.

### Application:

The surface must be clean, dry, degreased and matted. Thoroughly mix putty and 2-3% of hardener BPO by weight. Apply within 5 - 7 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

### Note:

Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C.

### Technical data:

Density: 0,98 - 1,00 g/cm<sup>3</sup>


Colour: beige



2004/42/IIIB(b)(250)<250




Cleaning  
60-010



BPO 2-3%



Pot life  
5-7 min 20°C



Latex / Nitril



16 -25 min. at 20°C




Hand sanding / dry:  
P150 - P320



Machine sanding / dry:  
P150 - P320



Shelf life:  
12 Month



Store in cool place

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.

Copyright: Q-Company 2017, all rights reserved.

Q-Company Int. GmbH / Beckershof 3 / D-24558 Henstedt-Ulzburg / Germany

Version: 02.01.2017