

Technical Datasheet

Q 70-265 2K UHS Clearcoat VOC 2:1

Characteristics:

Ultra high solid clear coat, thixotropic, good flow and UV resistant. High hardness, good chemical, mechanical and weathering resistance. Suitable for applications in spray booth. Clear coat is designed for use on solvent- and waterborne base coat.

Application:

Mixing ratio: 2:1 by volume. Mix thoroughly.

Apply with a spray gun with nozzle diameter 1,2 mm in 2 normal coats with 10 min. flash off between the coats.

Technical data:

VOC content: 2004/42/IIB(d)(420) 385

Clear coat 70-265:

Shelf-life: 12 months Density: 0,96 g/cm³ Colour: clear


Hardener normal 70-265HN - Hardener fast 70-265HF:

Shelf-life: 12 months Density: 1,00 g/cm³ Colour: colourless/slightly yellow

Note: Possible light coloration of the hardener doesn't affect the shade of the finishing



clear



2 : 1



0 -10%



40 min 20°C



19-20 s 4mm DIN



Q-99-100



1,2 mm
2 coats 45-50 my



7-10 min <> coat



HN 60°C. 30 min
HN 20°C. 9 h
HF 60°C. 20 min
HF 20°C. 6 h



15 min



P1000 - P2500



12 month



2004/42/IIB(d)(420) 385

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.

Copyright: Q-Company 2017, all rights reserved.

Q-Company Int. GmbH / Beckershof 3 / D-24558 Hennstedt-Ulzburg / Germany

Version: 02.01.2017